



Polystyrene Particles-CY3 PRODUCT DATA SHEET

Polystyrene Particles-CY3

Description

Abvigen has developed a large selection of polystyrene micro- and nanoparticles. Polystyrene particles and Microparticles are highly spherical plastic particles in sizes between 50 nm to 100 um. The polystyrene particles are prepared by using emulsion polymerization process. Coated or conjugated particles are prepared either by passive adsorption or covalent coupling.

For custom sizes, formulations or bulk quantities please contact our customer service department.

website: www.abvigen.com Phone: +1 929-202-3014 Email: info@abvigenus.com

Characteristics

Core diameter: 50 nm -100 um

Size: 10 ml; 20 ml; 50 ml; 100 ml

Concentration: 10 mg/ml

Shape: Spherical

Density: 1.03 g/ccm

Composition: Polystyrene Particles

Fluorescence: CY3

Buffer: DI Water

Form: Suspension

Store: Storage at 2 - 8 °C. **DO NOT FREEZE.**

Storage

This product should be stored at 2-8°C. **DO NOT FREEZE.**

Highlights

Highly monodisperse

Reproducibility

1378 US-206 Ste 6-126, Skillman, NJ USA

info@abvigenus.com

Tel: 1-816-388- 0112 Fax: 1- 888-616-0161

Reserved

Email:

© Abvigen Inc All Rights



Stable and resistant to aggregation

Versatility

Highly uniform in size and shape

Easy visualization

Low toxicity with good biocompatibility

For 10 mg/ml of Polystyrene Particles

Diameter	Conc. mg/ml	Particles/mg	Particles/ml	Diameter	Conc. mg/ml	Particles/mg	Particles/ml
25 nm	10	1.19E+14	1.19E+15	10 um	10	1.85E+06	1.85E+07
50 nm	10	1.48E+13	1.48E+14	20 um	10	2.32E+05	2.32E+06
80 nm	10	3.62E+12	3.62E+13	30 um		6.87E+04	6.87E+05
100 nm	10	1.85E+12	1.85E+13	40 um	10	2.90E+04	2.90E+05
200 nm	10	2.32E+11	2.32E+12	50 um	10	1.48E+04	1.48E+05
300 nm	10	6.87E+10	6.87E+11	60 um	10	8.58E+03	8.58E+04
400 nm	10	2.90E+10	2.90E+11	70 um	10	5.41E+03	5.41E+04
500 nm	10	1.48E+10	1.48E+11	80 um	10	3.62E+03	3.62E+04
600 nm	10	8.58E+09	8.58E+10	90 um	10	2.54E+03	2.54E+04
700 nm	10	5.41E+09	5.41E+10	100 um	10	1.85E+03	1.85E+04
800 nm	10	3.62E+09	3.62E+10	200 um	10	2.32E+02	2.32E+03
900 nm	10	2.54E+09	2.54E+10	300 um	10	6.87E+01	6.87E+02
1 um	10	1.85E+09	1.85E+10	400 um	10	2.90E+01	2.90E+02
2 um	10	2.32E+08	2.32E+09	500 um	10	1.48E+01	1.48E+02
3 um	10	6.87E+07	6.87E+08	600 um	10	8.58E+00	8.58E+01
4 um	10	2.90E+07	2.90E+08	700 um	10	5.41E+00	5.41E+01
5 um	10	1.48E+07	1.48E+08	800 um	10	3.62E+00	3.62E+01
6 um	10	8.58E+06	8.58E+07	900 um	10	2.54E+00	2.54E+01
7 um	10	5.41E+06	5.41E+07	1 mm	10	1.85E+00	1.85E+01
8 um	10	3.62E+06	3.62E+07	3 mm	10	6.87E-02	6.87E-01
9 um	10	2.54E+06	2.54E+07				

1378 US-206 Ste 6-126, Skillman, NJ USA

Email:

info@abvigenus.com

Tel: 1-816-388- 0112 Fax: 1- 888-616-0161

© Abvigen Inc All Rights

Reserved



Ordering Information

website: www.abvigen.com

Phone: +1 929-202-3014

Email: info@abvigenus.com

1378 US-206 Ste 6-126, Skillman, NJ USA

info@abvigenus.com

Tel: 1-816-388-0112 Fax: 1-888-616-0161

Reserved

Email:

© Abvigen Inc All Rights