



Endotoxin Free Gold NanoUrchins PRODUCT DATA SHEET

Endotoxin Free Gold NanoUrchins

Description

Endotoxin Free Gold NanoUrchins have unique optical properties compared to spherical gold nanoparticles of the same core diameter. The spiky uneven surface causes a red shift in the surface plasmon peak and a larger enhancement of electromagnetic fields at the tips of the Gold NanoUrchin spikes compared to that of a spherical particle. As an example, 100 nm spherical gold nanoparticles have an SPR peak at 570 nm while 100 nm Gold NanoUrchins have a SPR peak at around 680 nm.

In addition, binding of ligands such as proteins to the Gold NanoUrchin surface causes a larger shift in the surface plasmon peak compared to standard spherical gold nanoparticles. The citrate-covered surface of our Gold NanoUrchins allows for efficient adsorption of primary antibodies and other proteins. In addition, Gold NanoUrchins can be further modified and functionalized through ligand-exchange with e.g. thiol-containing ligands such as PEG and oligonucleotides.

These particles can be used as an alternative to standard spherical gold nanoparticles in a wide range of applications such as electron microscopy, immunostaining and development of biological sensors. Our Gold NanoUrchins are available in 6 different sizes and have uniform size distribution (CV < 12%). All of our batches go through stringent quality control prior to shipment to our customers using dynamic light scattering to guarantee size and monodispersity and lot specifications are supplied with each product. The endotoxin levels of all batches are validated by the Limulus amoebocyte lysate (LAL) test and do not exceed 0.5EU/mL.

Product List

Cat No	Product Name	Concentration	Size
AEFGNU-50	Endotoxin Free Gold NanoUrchins, 50 nm	OD 1	20 mL
AEFGNU-60	Endotoxin Free Gold NanoUrchins, 60 nm	OD 1	20 mL
AEFGNU-70	Endotoxin Free Gold NanoUrchins, 70 nm	OD 1	20 mL
AEFGNU-80	Endotoxin Free Gold NanoUrchins, 80 nm	OD 1	20 mL
AEFGNU-90	Endotoxin Free Gold NanoUrchins, 90 nm	OD 1	20 mL
AEFGNU-100	Endotoxin Free Gold NanoUrchins, 100 nm	OD 1	20 mL



For custom sizes, formulations or bulk quantities please contact our customer service department.

Website: www.abvigen.com Phone: +1 929-202-3014 Email: info@abvigenus.com

Characteristics

Composition: Citric acid stabilized Gold NanoUrchins

Core size range: 50 nm ~ 100 nm (Coefficient of Variance < 12%)

Polydispersity Index (PDI): < 0.20

Concentration: OD=1 (~ 0.05 mg/ml)

Absorbance (λ_{max}): 585 ~ 680 nm (core diameter dependant)

Formulation: Supplied in 0.1 mM Phosphate-Buffered Saline (0.01X PBS)

Features

Enhanced optical properties

Endotoxin-free as tested by the Limulus amoebocyte lysate (LAL) test for endotoxins and determined to be < 0.5 EU/mL, whilst also being free from substances that interfere with the endotoxin testing reaction.

Packaged with dust-free protection to maintain the highest level of sterility, also making them suitable for use in clean rooms

Readily adsorbs proteins to the surface

Ideal for cellular and cellular toxicity studies, immunological studies, experimental models, and aseptic assays

Applications

Ideal for development of peptide and protein gold conjugates for use in applications such as blotting, lateral flow assays, LSPR assays, light microscopy, and transmission electron microscopy (TEM).

Ideal for cellular and cellular toxicity studies.

For OD 1 of Endotoxin Free Gold NanoUrchins

Diameter /nm	Conc. mg/ml	Particles/mg	Particles/ml	Diameter /nm	Conc. mg/ml	Particles/mg	Particles/ml
50	0.05	7.91E+11	3.95E+10	80	0.05	1.93E+11	9.65E+09
60	0.05	4.58E+11	2.29E+10	90	0.05	1.36E+11	6.78E+09
70	0.05	2.88E+11	1.44E+10	100	0.05	9.89E+10	4.94E+09



Storage

Store product away from direct sunlight at 4-25°C. Lower temperature prolongs the shelf life of the product.

DO NOT FREEZE. Freezing causes irreversible aggregation of the Gold NanoUrchins.

If stored unopened and as specified, Abvigen gold nanourchins are stable for at least 6 months.

Handling

When stored for a long period of time gold nanourchins may sediment at the bottom of the flask, which is especially true for larger particle sizes. Prior to use, re-suspend the sedimented particles by swirling until a homogenous solution is obtained.

To maintain optimal performance, and stability of the colloidal gold, care should be taken to use clean storage containers if using other than supplied with the product.

Washing Gold Nanoparticles

Although it is not generally necessary to wash the gold nanourchins prior to use, some applications may require additional washing procedures. The easiest way to remove possible contaminants in the nanoparticles solution is by centrifugation. Centrifugation force is dependent on size of the gold nanourchins and should be adjusted according to Table I for optimal performance.

Note I: Since non-functionalized gold nanourchins are sensitive to salt containing buffers, re-suspension should always be performed in ultra-pure water to prevent irreversible aggregation. Irreversible aggregation is characterized by a clear to bluish solution upon the addition of salt.

Note II: Please note that centrifugation can induce aggregation. To prevent aggregation, it may be necessary to add Tween 20 at a concentration of 0.025% w/v.

Procedure

1. Place 1 ml aliquot of gold nanourchins in a 1.5 ml micro centrifuge tube.
2. Centrifuge the gold nanourchins for 30 min using the appropriate G force determined by referencing Table I.
3. Remove the supernatant and re-suspend in an appropriate volume of ultra-pure water.
4. Vortex to re-disperse the particles.



Table I. Appropriate G forces for centrifugation of gold nanourchins. Note that recommended conditions are for a volume of 1 ml and centrifugation using a microcentrifuge.

Size (nm)	Speed (g)	Time (min)
50	2000	30
60	1125	30
80	600	30
100	400	30

Notes

This product is for R&D use only, not for drug, household, or other uses.

Ordering Information

Website: www.abvigen.com

Phone: +1 929-202-3014

Email: info@abvigenus.com