




Silica Coated Gold Particles-PEI PRODUCT DATA SHEET

Silica Coated Gold Particles-PEI

Description

Silica Coated Gold Particles is a composite nanomaterial composed of Gold Particles coated with a silica shell. This composite nanomaterial exhibits the Surface Enhanced Raman Scattering effect of Gold Particles and excellent biocompatibility of silica. The presence of silica shell enhances the stability of Gold Particles while reducing their cytotoxicity. Silica shell has good chemical modification effect, and by modifying the surface of silica layer with PEI, Silica Coated Gold Particles-PEI can be obtained. PEI is a cationic polyamine polymer with a large number of amino groups, which can interact with negatively charged nucleic acids to form stable complexes and enhance the dispersibility of Silica Coated Gold Particles. Silica Coated Gold Particles-PEI has a wide range of applications in fields such as biosensing, molecular imaging, drug delivery, photothermal therapy, and catalysis.



Abvigen Inc can provide high-quality Silica Coated Gold Particles-PEI with a variety of particle sizes. The thickness of the silica shell layer can be selected, the particle size is uniform, and the stability is good. It can meet the personalized material needs of various customers in research and development, testing, production, and consumption.



For custom sizes, formulations or bulk quantities please contact our customer service department.

Website: www.abvigen.com Phone: +1 929-202-3014 Email: info@abvigenus.com

Characteristics

OD: 50

Size: 1 ml or others

Diameter: 1.8 nm - 1500 nm

Surface: PEI

Shape: Spherical

Composition: Silica Coated Gold Particles

Silica Thickness: 3 nm/ 5 nm/ 10 nm/ 20 nm/ 30 nm

Buffer: DI Water

Monodispersity: > 99.9%

Store: Storage at 4 °C

For 50 OD of Silica Coated Gold Particles-PEI

Cat No	Diameter (nm)	Peak SPR Wavelength (nm)	NPS/ml	Molarity (pM)	Moles	Molar Ext. (M-1cm-1)
ASCGN-1.8	1.8	—	4.25E+16	7.10E+07	7.09E-08	7.05E+05
ASCGN-2.2	2.2	—	2.33E+16	3.90E+07	3.88E-08	1.29E+06
ASCGN-3	3	—	9.19E+15	1.50E+07	1.53E-08	3.26E+06
ASCGN-4	4	—	3.88E+15	6.50E+06	6.46E-09	7.74E+06
ASCGN-5	5	512	1.99E+15	3.30E+06	3.31E-09	1.51E+07
ASCGN-10	10	516	2.48E+14	4.10E+05	4.14E-10	1.21E+08
ASCGN-15	15	518	7.35E+13	1.20E+05	1.23E-10	4.08E+08
ASCGN-20	20	520	3.10E+13	5.20E+04	5.17E-11	9.67E+08
ASCGN-25	25	521	1.59E+13	2.60E+04	2.65E-11	1.89E+09
ASCGN-30	30	523	9.19E+12	1.50E+04	1.53E-11	3.26E+09
ASCGN-35	35	526	5.79E+12	9.60E+03	9.65E-12	5.18E+09
ASCGN-40	40	527	3.88E+12	6.50E+03	6.46E-12	7.74E+09
ASCGN-45	45	529	2.72E+12	4.50E+03	4.54E-12	1.10E+10
ASCGN-50	50	531	1.99E+12	3.30E+03	3.31E-12	1.51E+10



ASCGN-55	55	533	1.49E+12	2.50E+03	2.49E-12	2.01E+10
ASCGN-60	60	536	1.15E+12	1.90E+03	1.91E-12	2.61E+10
ASCGN-65	65	539	9.04E+11	1.50E+03	1.51E-12	3.32E+10
ASCGN-70	70	542	7.23E+11	1.20E+03	1.21E-12	4.15E+10
ASCGN-75	75	545	5.88E+11	9.80E+02	9.80E-13	5.10E+10
ASCGN-80	80	549	4.85E+11	8.10E+02	8.08E-13	6.19E+10
ASCGN-85	85	553	4.04E+11	6.70E+02	6.73E-13	7.42E+10
ASCGN-90	90	558	3.40E+11	5.70E+02	5.67E-13	8.81E+10
ASCGN-95	95	563	2.89E+11	4.80E+02	4.82E-13	1.04E+11
ASCGN-100	100	569	2.48E+11	4.10E+02	4.14E-13	1.21E+11
ASCGN-150	150	612	7.35E+10	1.20E+02	1.23E-13	4.08E+11
ASCGN-200	200	—	3.10E+10	5.20E+01	5.17E-14	9.67E+11
ASCGN-500	500	—	1.99E+09	3.30E+00	3.31E-15	1.51E+13
ASCGN-1000	1000	—	2.48E+08	4.10E-01	4.14E-16	1.21E+14
ASCGN-1500	1500	—	7.35E+07	1.20E-01	1.23E-16	4.08E+14

Advantage

Good chemical stability

Strong photothermal conversion ability

Uniform particle size

Good biocompatibility

Surface modifiable

Applications

Spectral signal enhancement

Biosensor materials

Molecular imaging

Drug delivery

Chemical catalysis

Storage

1378 US-206 Ste 6-126, Skillman, NJ USA

Tel: 1-816-388- 0112 Fax: 1- 888-616-0161

Email: info@abvigenus.com

© Abvigen Inc All Rights Reserved



This product should be stored at 4°C. **DO NOT FREEZE.**

Ordering Information

Website: www.abvigen.com

Phone: +1 929-202-3014

Email: info@abvigenus.com