




Silica Coated Gold Particles-CTAB PRODUCT DATA SHEET

Silica Coated Gold Particles-CTAB

Description

Silica Coated Gold Particles is a composite nanomaterial composed of Gold Particles coated with a silica shell. This composite nanomaterial exhibits the surface enhanced Raman scattering effect of Gold Particles and excellent biocompatibility of silica. The presence of silica shell enhances the stability of Gold Particles while reducing their toxicity to cells. Silica shell has good chemical modification effect. By modifying the surface of silica layer with CTAB, Silica Coated Gold Particles-CTAB can be obtained. CTAB molecules have cationic properties, which give the modified Gold Particles a positive charge on their surface, further improving their dispersibility and stability in solvents. Silica Coated Gold Particles-CTAB can be used for drug delivery, biological immune detection, protein labeling, dark field optical imaging, fluorescence enhancement, surface enhanced Raman substrates, and other applications.



Abvigen Inc can provide high-quality Silica Coated Gold Particles-CTAB with a variety of particle sizes. The thickness of the silica shell layer can be selected, the particle size is uniform, and the stability is good. It can meet the personalized material needs of various customers in research and development, testing, production, and consumption.



For custom sizes, formulations or bulk quantities please contact our customer service department.

Website: www.abvigen.com Phone: +1 929-202-3014 Email: info@abvigenus.com

Characteristics

OD: 50

Size: 1 ml or others

Diameter: 1.8 nm - 1500 nm

Surface: CTAB

Shape: Spherical

Composition: Silica Coated Gold Particles

Silica Thickness: 3 nm/ 5 nm/ 10 nm/ 20 nm/ 30 nm

Buffer: DI Water

Monodispersity: > 99.9%

Store: Storage at 4 °C

For 50 OD of Silica Coated Gold Particles-CTAB

Cat No	Diameter (nm)	Peak SPR Wavelength (nm)	NPS/ml	Molarity (pM)	Moles	Molar Ext. (M-1cm-1)
ASCGN-1.8	1.8	—	4.25E+16	7.10E+07	7.09E-08	7.05E+05
ASCGN-2.2	2.2	—	2.33E+16	3.90E+07	3.88E-08	1.29E+06
ASCGN-3	3	—	9.19E+15	1.50E+07	1.53E-08	3.26E+06
ASCGN-4	4	—	3.88E+15	6.50E+06	6.46E-09	7.74E+06
ASCGN-5	5	512	1.99E+15	3.30E+06	3.31E-09	1.51E+07
ASCGN-10	10	516	2.48E+14	4.10E+05	4.14E-10	1.21E+08
ASCGN-15	15	518	7.35E+13	1.20E+05	1.23E-10	4.08E+08
ASCGN-20	20	520	3.10E+13	5.20E+04	5.17E-11	9.67E+08
ASCGN-25	25	521	1.59E+13	2.60E+04	2.65E-11	1.89E+09
ASCGN-30	30	523	9.19E+12	1.50E+04	1.53E-11	3.26E+09
ASCGN-35	35	526	5.79E+12	9.60E+03	9.65E-12	5.18E+09
ASCGN-40	40	527	3.88E+12	6.50E+03	6.46E-12	7.74E+09
ASCGN-45	45	529	2.72E+12	4.50E+03	4.54E-12	1.10E+10
ASCGN-50	50	531	1.99E+12	3.30E+03	3.31E-12	1.51E+10



ASCGN-55	55	533	1.49E+12	2.50E+03	2.49E-12	2.01E+10
ASCGN-60	60	536	1.15E+12	1.90E+03	1.91E-12	2.61E+10
ASCGN-65	65	539	9.04E+11	1.50E+03	1.51E-12	3.32E+10
ASCGN-70	70	542	7.23E+11	1.20E+03	1.21E-12	4.15E+10
ASCGN-75	75	545	5.88E+11	9.80E+02	9.80E-13	5.10E+10
ASCGN-80	80	549	4.85E+11	8.10E+02	8.08E-13	6.19E+10
ASCGN-85	85	553	4.04E+11	6.70E+02	6.73E-13	7.42E+10
ASCGN-90	90	558	3.40E+11	5.70E+02	5.67E-13	8.81E+10
ASCGN-95	95	563	2.89E+11	4.80E+02	4.82E-13	1.04E+11
ASCGN-100	100	569	2.48E+11	4.10E+02	4.14E-13	1.21E+11
ASCGN-150	150	612	7.35E+10	1.20E+02	1.23E-13	4.08E+11
ASCGN-200	200	—	3.10E+10	5.20E+01	5.17E-14	9.67E+11
ASCGN-500	500	—	1.99E+09	3.30E+00	3.31E-15	1.51E+13
ASCGN-1000	1000	—	2.48E+08	4.10E-01	4.14E-16	1.21E+14
ASCGN-1500	1500	—	7.35E+07	1.20E-01	1.23E-16	4.08E+14

Advantage

Good chemical stability

Strong photothermal conversion ability

Uniform particle size

Good biocompatibility

Surface modifiable

Applications

Spectral signal enhancement

Biosensor materials

Molecular imaging

Drug delivery

Chemical catalysis

Storage

1378 US-206 Ste 6-126, Skillman, NJ USA

Tel: 1-816-388- 0112 Fax: 1- 888-616-0161

Email: info@abvigenus.com

© Abvigen Inc All Rights Reserved



This product should be stored at 4°C. **DO NOT FREEZE.**

Ordering Information

Website: www.abvigen.com

Phone: +1 929-202-3014

Email: info@abvigenus.com