




Conjugated Gold Nanorods for Click Chemistry-DBCO PRODUCT DATA SHEET

Conjugated Gold Nanorods for Click Chemistry-DBCO

Description

Conjugated Gold Nanorods for Click Chemistry DBCO is a type of nanocomposite material prepared by conjugating dibenzocyclooctyne onto the surface of gold nanorods through polyethylene glycol, widely used in click chemistry. This material has excellent high temperature resistance, salt resistance, acid and alkali resistance, as well as excellent load capacity, making it suitable for use in complex chemical environments. Dibenzocyclooctyne has high reactivity and can participate in various chemical reactions. It can also be further chemically modified by introducing different functional groups to Gold Nanorods. Conjugated Gold Nanorods for Click Chemistry DBCO are widely used in fields such as diagnosis and imaging, exhibiting high sensitivity and selectivity in sensor applications, and can effectively detect and identify specific molecules or ions. In addition, Conjugated Gold Nanorods for Click Chemistry DBCO also have important value in the biomedical field. The material has good biocompatibility, surface functionalization, and can bind to various biomolecules, fluorescent dyes, or other functional groups. It is often used as a drug carrier or bioimaging agent and has good application prospects.



Abvigen Inc can provide high-quality Conjugated Gold Nanorods for Click Chemistry-DBCO in various particle sizes. This product has uniform particle size and good chemical reactivity on the surface, suitable for click chemistry, and can meet various personalized material needs such as customer research and development, testing, and production consumption.



For custom sizes, formulations or bulk quantities please contact our customer service department.

Website: www.abvigen.com Phone: +1 929-202-3014 Email: info@abvigenus.com

Characteristics

OD value: 50 OD

Size: 1 g

Polymer Bridge: 10 PEG, 1K PEG, 3K PEG, 5K PEG, 20K PEG

Surface: Dibenzocyclooctyne

Composition: Conjugated Gold Nanorods

Buffer: DI Water

Form: Suspension

Store: Storage at 2 - 8 °C

Storage

This product should be stored at 4°C. **DO NOT FREEZE.**

Properties of Conjugated Gold Nanorods for Click Chemistry-DBCO

Diameter (nm)	Length (nm)	Peak SPR Wave (nm)	Peak LSPR Wave (nm)	Nanorods /mL	Wt. conc (ug/ml)	Peak SPR (nm)
5	21	808	510	2.39E+14	1750	794-829
5	19	780	510	2.67E+14	1750	765-794
5	15	700	510	3.47E+14	1750	675-725
10	175	2100	510	6.73E+12	1750	1900-2300
10	102	1400	510	1.17E+13	1750	1300-1500
10	81	1200	510	1.48E+13	1750	1132-1300
10	67	1064	510	1.81E+13	1750	1022-1132
10	59	980	510	2.09E+13	1750	965-1022
10	55	950	510	2.22E+13	1750	925-965
10	50	900	510	2.47E+13	1750	875-925
10	45	850	510	2.78E+13	1750	829-875
10	41	808	510	3.10E+13	1750	794-829
10	38	780	510	3.36E+13	1750	765-794

10	35	750	510	3.70E+13	1750	725-765
10	29	700	510	4.44E+13	1750	675-725
10	24	650	510	5.55E+13	1750	625-675
10	19	600	510	7.40E+13	1750	575-625
25	245	1400	514	1.12E+12	2500	1232-1500
25	137	1064	514	2.05E+12	2500	1022-1232
25	119	980	514	2.39E+12	2500	965-1022
25	102	950	514	2.82E+12	2500	925-965
25	96	900	514	3.01E+12	2500	875-925
25	93	850	514	3.12E+12	2500	829-875
25	90	808	514	3.24E+12	2500	794-829
25	87	780	514	3.36E+12	2500	765-794
25	85	750	514	3.45E+12	2500	725-765
25	75	700	514	3.96E+12	2500	675-725
25	71	650	514	4.22E+12	2500	625-675
25	57	600	514	5.43E+12	2500	575-625
25	34	550	514	1.01E+13	2500	525-575
40	208	850	520	5.30E+11	2500	1022-1232
40	180	850	520	6.19E+11	2500	875-1022
40	148	850	520	7.67E+11	2500	829-875
40	134	808	520	8.56E+11	2500	794-829
40	124	780	520	9.33E+11	2500	765-794
40	112	750	520	1.05E+12	2500	725-765
40	92	700	520	1.31E+12	2500	675-725
40	80	650	520	1.55E+12	2500	625-675
40	68	600	520	1.89E+12	2500	575-625
40	60	550	520	2.21E+12	2500	525-575
50	245	1064	530	2.89E+11	2500	980-1232
50	145	808	530	5.15E+11	2500	750-850
50	110	700	530	7.08E+11	2500	650-750
50	100	600	530	7.93E+11	2500	550-650